

## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau(43) International Publication Date  
24 December 2003 (24.12.2003)

PCT

(10) International Publication Number  
**WO 03/106726 A1**

- (51) International Patent Classification<sup>7</sup>: **C22C 38/04**, 38/00, C21D 8/02, 8/04
- (21) International Application Number: PCT/JP03/02672
- (22) International Filing Date: 6 March 2003 (06.03.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
2002-170926 12 June 2002 (12.06.2002) JP
- (71) Applicant (for all designated States except US): **NIPPON STEEL CORPORATION** [JP/JP]; 6-3, Otemachi 2-chome, Chiyoda-ku, Tokyo 100-8071 (JP).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **MURAKAMI, Hidekuni** [JP/JP]; C/O NIPPON STEEL CORPORATION YAWATA WORKS, 1-1, Tobihata-cho, Tobata-ku, Kitakyushu-shi, Fukuoka 804-8501 (JP). **NISHIMURA, Satoshi** [JP/JP]; C/O NIPPON STEEL CORPORATION YAWATA WORKS, 1-1, Tobihata-cho, Tobata-ku, Kitakyushu-shi, Fukuoka 804-8501 (JP).
- (74) Agents: **ISHIDA, Takashi** et al.; A. AOKI, ISHIDA & ASSOCIATES, Toranomon 37 Mori Bldg., 5-1, Toranomon 3-chome, Minato-ku, Tokyo 105-8423 (JP).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**  
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: STEEL SHEET FOR VITREOUS ENAMELING AND PRODUCTION METHOD

(57) Abstract: To provide a non-aging steel sheet for vitreous enameling, the steel sheet being excellent in resistance to bubbles and black spots, without the employment of decarbonization and denitrification annealing that raises the cost of production and also without the addition of expensive elements such as Nb, Ti, etc. that raise the cost of alloys. The steel sheet comprises, in mass, to C: 0.0050% or less, Si: 0.50% or less, Mn: 0.005 to 1.0%, P: 10x(B-11/14xN) to 0.10%, S: 0.080% or less, Al: 0.050% or less, N: 0.0005 to 0.020%, B: 0.60xN to 0.020%, and O: 0.002 to 0.0800%, and the shape of B nitrides is controlled mainly by adjusting hot-rolling conditions.